

This spec sheet has been updated to reflect the removal of flame retardants.

Bronte

GENERAL SPECIFICATIONS

SURFACE COMPOSITION100% PVCSUBSTRATE COMPOSITION100% PolyesterWEIGHT32.oz per linear yard

 WIDTH
 54"

 THICKNESS
 1.00 mm

ADDED PERFORMANCE SPECIFICATIONS

STAIN RESISTANCE Yes

UV RESISTANCE 1,000 Hours ASTM G26-96 Method C

BLEACH RESISTANCE Yes, 10% Dilution

MILDEW RESISTANCEPassASTM G21-13COLD CRACK-20° FCFFA-6a-2007

SULFIDE STAIN RESISTANCE Yes

PHYSICAL PERFORMANCE SPECIFICATIONS

 ABRASION RESISTANCE
 500,000+ Double Rubs*
 ASTM D4157-07

 BREAKING STRENGTH
 89.2 Warp, 103 Fill
 ASTM D751-06

 FLEX RESISTANCE
 25,000+
 ASTM D2097-03

 TEAR STRENGTH: TONGUE TEAR
 25.8 Warp, 28 Fill
 ASTM D751-06

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13 Pass
UFAC CLASS I Pass
NFPA 260 Pass
FMVSS 302 Pass

REDUCED ENVIRONMENTAL IMPACT

NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT LEAD / HEAVY METAL FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS









*ACT® Registered Certification Marks